

G-STAR RAW

RESTRICTED SUBSTANCE LIST & PACKAGING RSL

VERSION 5.0 - March 2024

Table of contents version 5.0			
INTRODUCTION		PAGE	
INTRODUCTION		3	
SUPPLIER RESPONSIBILITY		5	
DEFINITION MATERIAL TYPE		6-7	
RISK MATRIX		PAGE	
RISK MATRIX APPAREL & FOOTWEAR		8-9	
RISK MATRIX PACKAGING		10	
RESTRICTED SUBSTANCES LIST 5.0		PAGE	
ACETOPHENONE AND 2- PHENYL-2-PROPANOL		11	
ACIDIC AND ALKALINE SUBSTANCES		11	
ALKYLPHENOLS (AP) AND ALKYPHENOL ETHOXYLATES (APEO)		12	
AZO-AMINES AND ARYLAMINE SALTS		13	
BIOCIDES		14	
BISPHENOLS		15	
CHLORINATED PARAFFINS		15	
CHLOROPHENOLS		16	
CHLORINATED BENZENES AND TOLUENES		17	
DIMETHYLFUMARATE (DMFu)		18	
DISPERSE DYES WHICH ARE CLASSIFIED TO BE ALLERGENIC		19	
DYES WHICH ARE CLASSIFIED TO BE CARCINOGENIC		20	
DYES NAVY BLUE		20	
FLAME RETARDANTS		21	
FLUORINATED GREENHOUSE GASES		22	
FORMALDEHYDE		22	
HEAVY METALS EXTRACTABLE		23-24	
HEAVY METALS TOTAL CONTENT		24	
HEAVY METALS RELEASABLE NICKEL		25	
MONOMERS		25	
RESTRICTED SUBSTANCES LIST 5.0 CONTINUED		PAGE	
N-NITROSAMINES		26	
ORGANOTIN COMPOUNDS		27	
ORTHO-PHENYLPHENOL (OPP)		27	
OZONE DEPLETING SUBSTANCES		27	
PER-AND POLYFLUOROALKYL SUBSTANCES (PFAS) (SEE APPENDIX A)		28	
PESTICIDES AGRICULTURAL (SEE APPENDIX B)		29	
PHthalATES		29-30	
POLYCYCLIC AROMATIC HYDROCARBONS (PAHs)		31	
QUINOLINE		31	
RESTRICTION ON PACKAGING		32	
SOLVENTS AND RESIDUALS		32	
UV ABSORBERS / STABILISERS		33	
VOLATILE ORGANIC COMPOUNDS (VOCs)		33	
APPENDIX RESTRICTED SUBSTANCES LIST		PAGE	
APPENDIX A. PERFLUORINATED AND POLYFLUORINATED CHEMICALS (PFCS)		34-35	
APPENDIX B. PESTICIDES AND HERBICIDES, AGRICULTURAL		36	
REACH REGULATION 1907/2006		PAGE	
REACH CANDIDATE LIST/AUTHORIZATION LIST		37	
GENERAL		PAGE	
DECLARATION OF CONFORMITY		38	
CHANGE LOG		39-40	
DISCLAIMER		41	

Introduction version 5.0

INTRODUCTION

G-Star is committed to producing high quality and responsibly manufactured products and intends to only do business with suppliers that share our commitment to make a strong product in a socially and environmentally conscious way. We outlined the minimum Social and Environmental, Health & Safety (EHS) standards under which our products should be manufactured in the G-Star Supplier Code of Conduct. The Code of Conduct refers to the G-Star Restricted Substances List (RSL) and Manufacturing Restricted Substances List (MRSL) as the basis for monitoring the use of chemicals in G-Star products.

The RSL applies to all products of G-Star Raw C.V. and/or its subsidiaries (hereinafter ‘G-Star’), which includes ready-made garments, non-apparel, accessories and packing materials. The RSL also applies to all materials, such as metal parts and trims for use in producing G-Star products.

The MRSL applies to all chemicals used in wet processing facilities which includes dyeing, washing and printing facilities. Chemicals used in these production processes should meet the requirements of the MRSL.

The RSL and the MRSL should be communicated to all (raw material) suppliers. All chemicals used in any production process must meet the requirements of the G-Star MRSL and all products delivered to G-Star must meet the requirements of the RSL.

G-Star's Commitment

ZDHC & Supplier Detox Program

Through the DETOX Commitment with Greenpeace in 2013, G-Star committed to ban the use of hazardous chemicals from our products and production processes within our supply chain. This followed with G-Star becoming a signatory to the Zero Discharge of Hazardous Chemicals (ZDHC) initiative. The ZDHC signatory brands unite around a joint roadmap (Roadmap to Zero) to ensure safe and sustainable chemical use in the fashion industry. G-Star will continue to work with the ZDHC tools (please see below), as well as requiring the annual submission of a verified Higg Facility Environmental Module (FEM) to monitor the environmental performance in production and manufacturing of our garments in our so-called DETOX program.

As part of the DETOX program, all G-Star RAW's supply chain partners are required to follow ZDHC's latest Manufacturing Restricted Substances List (MRSL). Additionally, all wet factories generating on average, equal to, or more than 15m3 of industrial wastewater per day are required to:

- Generate InCheck reports monthly.
- Generate ClearStream reports 2x per year, following ZDHC's latest Wastewater Guidelines.
 - o 1x between 1st of May and 30th of October
 - o 1x between 1st of November and 30th of April
 - o Sampling, testing, and reporting can occur anytime during each reporting cycle, as long as there are at least three months between sample dates for the two reporting deadlines.
- Obtain a Supplier to Zero certificate.

MRSL and RSL Dynamics

The MRSL is a proactive tool used to manage the use of chemicals during manufacturing, aiming to minimize environmental impact and enhance worker safety. However, non-conformities in MRSL compliance can often indicate potential risks in meeting RSL standards, which focus on the safety of the final product for consumers.

Therefore, suppliers with identified MRSL non-conformities should anticipate the likelihood of additional testing for RSL compliance. This step is crucial to ensure that products meet global safety standards and regulations, and to maintain our commitment to product safety and environmental stewardship. We encourage our supply chain partners to proactively engage in resolving these challenges and to view this process as an integral part of responsible and sustainable production practices.



Purpose of the RSL
Our suppliers are critical partners in meeting our commitments regarding consumer safety, working conditions and environmental protection. The purpose of the RSL for garment and fabric manufacturing is to inform our suppliers on all chemicals that are banned or restricted in G-Star finished products. Our suppliers are expected to study this document carefully and communicate the information to relevant internal teams, sub-contractors and others involved in the production of G-Star products.
Each supplier is required to declare and ensure that the materials, parts, trims, metal parts and other goods supplied or otherwise delivered for G-Star products comply with the limitations described or referred to in the RSL and any additional requirements imposed by law or local authorities. The supplier is also responsible for seeking guidance from G-Star in situations of doubt about product compliance with the RSL for garment and fabric manufacturing.
Compliance with this Restricted Substance List is a mandatory condition for each and every order placed by G-Star.
G-Star Raw C.V. March 2024

Supplier Responsibility version 5.0
Supplier Responsibility
<p>G-Star wants to ensure that our products are manufactured in a social and environmental responsible way throughout the supply chain. As our supplier/partner you are committed to live up to the G-Star Supplier Code of Conduct and the Restricted Substance List (“RSL”). The supplier must ensure to be compliant with G-Star’s RSL by sourcing responsibly, this entails testing the items needed for the merchandise. We also advise you to use our nominated suppliers.</p>
<p>All Suppliers are required to:</p> <ul style="list-style-type: none"> • Ensure they are fully aware of the content and requirements of G-star Supplier Code of Conduct and RSL policies. • Sign and return scanned copy to QA responsible <u>the Declaration of Conformity Form</u> • Communicate to their supply chain on G-Star MRSL & RSL requirements. • Test / certify all materials/finished product in line with EU legislation and G-Star RSL. • Testing must be carried out by internationally accredited and independent laboratories. • Test reports must be kept at least 2 years as proof of due diligence. • Inform G-star QA about non-conformities, any risk to consumers or other incidents related to safety of their product immediately, and prepare corrective action plan to improve the non-conformity.
<p>Please be aware that buying from G-star nominated supplier does <u>not</u> shift the responsibility to this supplier; you as our direct supplier are fully responsible for every step in the production process, and for all materials used. This means you are responsible for the complete product including the packaging materials, placement prints and the ink used for them. Therefore all necessary control measures have to be in place to avoid that your merchandise fails to meet the requirements.</p> <p>In case of failure, which means not complying with G-Star’s RSL, the merchandise will not be accepted and the supplier will receive respective written information. There will be a fine to be paid by the supplier based on the damage G-Star suffered. We want to emphasize that we invest time, effort and money into these testing procedures and trust that you will ensure it will be handled correctly in your facilities to enable a long-term relationship with G-Star.</p> <p>If there are any questions or concerns, please feel free to reach out to RSL@g-star.com for further info regarding G-Star's RSL.</p>

Definition of Material type version 5.0		
Definition of Material type		
Natural fibers. Animal or vegetable fibers (including semi-synthetics).	Printing. The process of applying colour to a fabric in definite patterns or designs.	Foam. Spongy material made by trapping air bubbles in a solid. These can be open cell or closed cell
Blended fibers. Woven or knitted materials created by blending two or more fiber types. For the purpose of this RSL, a blended fiber consists of a natural and a synthetic fiber.	Natural materials. Material derived from animals or plants that have undergone very little modification. Includes horn, bone, cork, wood, paper, and straw. Excludes natural fibers, natural leather, feathers, down, and metals	Metals. Chemical elements that can be lustrous, ductile, malleable, and good conductors of heat and electricity. Includes metals deposited by physical vapor deposition (PVD), chemical vapor deposition (CVD), or electroplating
Synthetic fibers. Human-made fibers based on synthetic chemicals (often from petroleum sources) such as polymers and extruded fibers.	Crystal. In this variety of glass, also known as lead glass, lead replaces calcium content of a typical potash glass. The addition of lead oxide gives crystal a much higher index of refraction than normal glass, and consequently much greater sparkle. Crystal typically contains at least 24% lead and is therefore exempt from many regulatory requirements for jewelry. In the European Union, labeling of crystal products is regulated by Council Directive 69/493/EEC, which defines four categories based on the chemical composition and properties of the material.	Feathers and down. Includes the smaller down feathers as well as the larger contour and flight feathers. See the International Down and Feather Bureau for specific down and feather definitions.
Synthetic coated fabrics. Leather-like materials composed of a textile backing and, typically, a PU or PVC coating. May be referred to as artificial, imitation, vegan, or synthetic leather, or pleather	Polymers and plastics. Plastics are composed of various polymers (typically from petroleum sources) usually mixed with additives including colorants, plasticizers, stabilizers, and fillers. These additives affect the chemical composition, chemical properties, and mechanical properties of the plastic.	Glue. A substance capable of holding materials together by surface attachment.
Natural leather. Created by tanning animal rawhide	Natural rubber. Elastic material made from latex sap or trees that can be vulcanized.	
<p>Coating. A fluid, semi-fluid, or other material, with or without a suspension of finely divided coloring matter, which changes to a solid film when a thin layer is applied to a metal, wood, stone, paper, leather, cloth, plastic, or other surface.</p> <p>Coatings do not include printing inks or those materials which actually become a part of the substrate, such as the pigment in a plastic article or those materials which are actually bonded to the substrate, such as by electroplating or ceramic glazing. See 'synthetic coated fabrics' for leather like materials where the coating becomes part of the substrate.</p>	Synthetic rubber. Material made from petroleum-based monomers with properties similar to natural rubber.	

Definition of Material type version 5.0											
Definition of Material type											
Examples of Materials within the Scope of the G-Star RSL ¹											
Natural Fibers Including semi-synthetics	Blended Fibers	Synthetic Fibers	Synthetic coated fabrics	Natural Leather & Fur Skin	Coatings & Prints	Natural Materials	Other Materials	Polymers, Plastics, Foams, Natural Rubber & Synthetic Rubber	Metal	Feathers & Down	Glue
<ul style="list-style-type: none"> • Cotton • Wool • Silk • Hemp • Cashmere • Linen • Fur hair • Rayon (Semi-synthetic) • Lyocell (Semi-synthetic) 	<ul style="list-style-type: none"> • Cotton- Polyester • Wool-Nylon • Ramie- Polyester 	<ul style="list-style-type: none"> • Polyester • Acrylic • Nylon • Polyamide 	Textiles with: <ul style="list-style-type: none"> • Polyurethane (PU) • Polyvinyl Chloride (PVC)coating • Other Polymeric coatings 	<ul style="list-style-type: none"> • Leather • Fur skin • Bonded recycled leather 	Printing techniques such as: <ul style="list-style-type: none"> • Heat transfers • Dye sublimation printing • Screen printing • Direct-to- garment printing • Discharge printing • Plastisol transfers Coatings such as: <ul style="list-style-type: none"> • Polyvinyl chloride (PVC) • Polyurethane (PU) • UV-cured 	<ul style="list-style-type: none"> • Horn • Bone • Cork • Wood • Paper • Straw • Stone • Shell (e.g. coconut or mother of pearl) • Jacron (a semi-synthetic paper product) 	<ul style="list-style-type: none"> • Glass • Synthetic stone • Porcelain • Ceramic • Crystal 	<ul style="list-style-type: none"> • Ethylene vinyl acetate (EVA) • Polystyrene (PS) • Polyethylene (PE) • Acrylonitrile butadiene styrene (ABS) • Neoprene • Polypropylene (PP) • Polycarbonate (PC) • Polyamide (PA) • Polyurethane (PU) • Polyvinyl chloride (PVC) • Thermoplastic polyurethane (TPU) • Thermoplastic elastomer (TPE) • Styrene ethylene butylene styrene (SEBS) 	<ul style="list-style-type: none"> • Stainless steel • Brass • Copper • Gold • Silver • Aluminium 	<ul style="list-style-type: none"> • Feathers • Down 	<ul style="list-style-type: none"> • Hot melt adhesive • Powdered adhesive • Flock adhesive • Contact adhesive • Latex glue • Polyurethane glue • Neoprene cement • Epoxies • Silicone adhesive • UV-cured adhesive

¹ NOTE: This list provides examples of materials within each category but is not exhaustive

Risk Matrix Apparel and Footwear version 5.0																		
<p>●●● indicates a higher risk that a chemical is used and/or could be detected in a particular material.</p> <p>●● indicates a lower risk that a chemical is used and/or could be detected in a particular material.</p> <p>No dot indicates that the risk is not anticipated in a particular material.</p>																		
CHEMICAL	NATURAL FIBERS	SYNTHETIC FIBERS	NATURAL AND SYNTHETIC BLENDS	SYNTHETIC COATED FABRICS	NATURAL LEATHER & FUR SKIN	NATURAL MATERIALS	METAL	OTHER: PORCELAIN , CERAMIC , GLASS, CRYSTAL , ETC.	FEATHER & DOWN	POLYMERS							COATING AND PRINTS	GLUE
										EVA	PU Foams	All other PU & TPU	RUBBER - excludes latex and silicon rubbers	Polycarbonate	ABS	PVC		
ACETOPHENONE AND 2- PHENYL-2-PROPANOL										●●								
ACIDIC AND ALKALINE SUBSTANCES (pH)	●●●	●●●	●●●	●●●	●●●													
ALKYLPHENOL (AP) & ALKYLPHENOL ETHOXYLATES (APEOs), including all isomers	●●●	●●●	●●●	●●●	●●●	●●●			●●●	●●●	●●●	●●●	●●●	●●●	●●●	●●●	●●●	●●●
AZO AMINES AND ARYLAMINE SALTS	●●●/A	●●●/A	●●●/A	●●●/A	●●●/A	●●●/A			●●●/A								●●●	
BISPHENOLS		●●●	●●●	●●●	●●●					●●	●●	●●	●●	●●●	●●	●●	●●	
CHLORINATED PARAFFINS				●●/J	●●●					●●	●●	●●●	●●●	●●	●●	●●●	●●	
CHLOROPHENOLS	●●	●●	●●		●●													
CHLORINATED BENZENES AND TOLUENES		●●	●●	●●														
DIMETHYLFUMURATE (DMFu)					●●													
DYES DISPERSE DYES		●●●/A	●●●/A	●●●/A													●●	
DYES FORBIDDEN CARCINOGENIC DYES	●●/A	●●/A	●●/A	●●/A													●●	
DYES NAVY BLUE		●●	●●															
FLAME RETARDANTS	●●/B																	
FORMALDEHYDE	●●●	●●●	●●●	●●	●●●	●●●/C							●●				●●●	●●●
HEAVY METALS CHROMIUM VI	●●/D	●●/E			●●●													
HEAVY METALS EXTRACTABLE	●●●	●●●	●●●	●●	●●●		●●/F			●●	●●	●●	●●	●●	●●	●●	●●	
A ●●● for dyed/colored materials (non white only)	E ●● if extractable Chrome above 1 mg/kg							J ●●● for PVC materials otherwise ●●							N ●●● for PU and PVC-based materials			
B ●● if Flame Retardants are applied	F Copper is exempt from restriction limits in Metal parts.							K ●● for Styrene/Butadiene Rubbers (SBRs) only										
C ●●● for Wood, Paper, and Straw materials only	G●● for plant-based fibers; N/A for animal-based fibers.							L ●●● if PFAS use or contamination is expected										
D ●● for Wool materials only	H ●●● for Cadmium and Lead only; Crystal is exempt for Lead							M ●●● if Rubber or black Polymeric materials otherwise ●●										

Risk Matrix Apparel and Footwear version 5.0																			
<p>●●● indicates a higher risk that a chemical is used and/or could be detected in a particular material.</p> <p>●● indicates a lower risk that a chemical is used and/or could be detected in a particular material.</p> <p>No dot indicates that the risk is not anticipated in a particular material.</p>																			
CHEMICAL	NATURAL FIBERS	SYNTHETIC FIBERS	NATURAL AND SYNTHETIC BLENDS	SYNTHETIC COATED FABRICS	NATURAL LEATHER & FUR SKIN	NATURAL MATERIALS	METAL	OTHER: PORCELAIN , CERAMIC , GLASS, CRYSTAL , ETC.	FEATHER & DOWN	POLYMERS								COATING AND PRINTS	GLUE
										EVA	PU Foams	All other PU & TPU	RUBBER - excludes latex and silicon rubbers	Polycarbonate	ABS	PVC	All Other foams, plastics & Polymer		
HEAVY METALS RELEASABLE NICKEL							●●												
HEAVY METALS TOTAL CONTENT	●●/G		●●/G	●●●	●●		●●●	●●●/H		●●●	●●●	●●●	●●●	●●●	●●●	●●●	●●●	●●●	●●
MONOMERS, STYRENE & VINYL CHLORIDE				●●●/J									●●/K		●●	●●●		●●●/J	
N-NITROSAMINES													●●						
ORGANOTIN COMPOUNDS		●●	●●	●●●	●●						●●●	●●●	●●●			●●●	●●●	●●●	●●●
ORTHO-PHENYLPHENOL (OPP)	●●	●●	●●	●●	●●													●●	
PER- AND POLYFLUOROALKYL SUBSTANCES	●●●/L																		
PESTICIDES																			
PHTHALATES				●●●						●●●	●●●	●●●	●●●	●●	●●	●●●	●●●	●●●	●●●
POLYCLIC AROMATIC HYDROCARBONS				●●						●●●/M	●●●/M	●●●/M	●●●			●●●/M	●●●/M	●●●/M	●●●/M
QUINOLINE		●●	●●																
SOLVENTS / RESIDUALS DMFa				●●●							●●●	●●●						●●●/N	●●●/N
SOLVENTS / RESIDUALS DMAC AND NMP				●●●							●●	●●					●●	●●	●●
SOLVENTS / RESIDUALS FORMAMIDE										●●								●●	
UV ABSORBERS / STABILISERS										●●	●●	●●	●●	●●	●●	●●	●●		
VOLATILE ORGANIC COMPOUNDS (VOCs)				●●						●●	●●	●●	●●	●●	●●	●●	●●	●●	●●●
A ●●● for dyed/colored materials (non white only)	E ●● if extractable Chrome above 1 mg/kg							J ●●● for PVC materials otherwise ●●							N ●●● for PU and PVC-based materials				
B ●● if Flame Retardants are applied	F Copper is exempt from restriction limits in Metal parts.							K ●● for Styrene/Butadiene Rubbers (SBRs) only											
C ●●● for Wood, Paper, and Straw materials only	G●● for plant-based fibers; N/A for animal-based fibers.							L ●●● if PFAS use or contamination is expected											
D ●● for Wool materials only	H ●●● for Cadmium and Lead only; Crystal is exempt for Lead							M ●●● if Rubber or black Polymeric materials otherwise ●●											

Risk Matrix Packaging version 5.0

●●● indicates a high risk that a chemical is used and/or could be detected in a particular material.

●● indicates a medium risk that a chemical is used and/or could be detected in a particular material.

● indicates a low risk that a chemical is used and/or could be detected in a particular material.

No dot indicates that there is a negligible risk of a chemical being used and/or detected in a particular material.

SUBSTANCE	NATURAL FIBERS	BLENDED FIBERS	SYNTHETIC FIBERS	COATINGS, DYES & PRINTS	NATURAL MATERIALS including paper and cardboard	POLYMERS, PLASTICS, FOAMS, NATURAL RUBBER & SYNTHETIC RUBBER	METAL	GLUE	LEATHER Natural	LEATHER Artificial
ALKYPHENOL (AP) AND ALKYPHENOL ETHOXYLATES (APEO) including all isomers	●●●	●●●	●●●	●●●	●●●	●●●/A		●●●	●●●	●●●
AZO-AMINES AND ARYLAMINE SALTS	●●●/B	●●●/B	●●●/B		●●●/B				●●●/B	●●●/B
BISPHENOLS		●●●	●●●	●●●/C	●●●/D	●●/E			●●●	●●●
BUTYLHYDROXYTOLUENE (BHT)						●●/F				
DIMETHYLFUMARATE (DMFu)						●●/G			●●	
FORMALDEHYDE	●●	●●	●●	●●●	●●●	●●/H		●●●	●●	●●
HEAVY METALS TOTAL CONTENT (Cd, CrVI, Pb, Hg)*				●●	●●/J	●●/K	●●		●●	
MOSH/MOAH				●●●/L	●●●/M	●●●/L				
ORGANOTIN COMPOUNDS				●●●		●●●		●●●	●●	●●●
PER- AND POLYFLUOROALKYL SUBSTANCES (PFAS)	PROHIBITED									
PHthalATES				●●●/N		●●●/O		●●●	●●/P	●●●
A High risk for foams; Medium risk for other materials	F Medium risk for poly bags only; no testing requirement for other materials.					L High risk for printed packaging materials				
B High risk for dyed/colored materials (non-white) only	G Medium risk for silica gel packets and foam packaging only; no testing requirement for other materials					M High risk for recycled paper				
C High risk for PVC only; Level 2 for all other materials	H Medium risk for rubber only, no testing requirement for other materials					N High risk for plastisol prints; Medium risk for all other materials				
D High risk for thermal receipt and recycled paper only; Medium risk for other materials	J Medium risk for materials with high recycled content only; no testing requirement for other materials					O Medium risk for polycarbonate and ABS, Level 1 for all other polymers				
E Medium risk for tapes, polycarbonate, and recycled plastic cases only; no testing requirement for other materials	K Medium risk for PVC only, no testing requirement for other materials					P Medium risk for patent or coated leather; no testing requirement for other materials				

*Please note that Chromium VI, Cadmium, Lead, and Mercury are restricted to a sum total of 100 mg/kg in several jurisdictions. Cadmium, Lead, and Mercury are analyzed using the same method even if the risk of finding them varies across different materials.

Restricted Substances List version 5.0				
CHEMICAL SUBSTANCE	CAS NUMBER	TEST METHOD	G-STAR RESTRICTED LIMIT	RELEVANCE OF RESTRICTION
ACETOPHENONE AND 2- PHENYL-2-PROPANOL				
Acetophenone	98-86-2	Extraction in acetone or methanol GC/MS, sonication for 30 minutes at 60 degrees C	< 50 mg/kg each	Potential breakdown products in EVA foam when using certain cross-linking agents, including Dicumyl Peroxide.
2-Phenyl-2-Propanol	617-94-7			
ACIDIC AND ALKALINE SUBSTANCES				
pH value	N/A	Textiles and Synthetic coated fabrics: EN ISO 3071:2020: Leather: EN ISO 4045:2018	Textiles: 4.0–7.5 Leather: Chrome-tanned: 3.2 - 4.5 Other: 3.5-7.0	<p>pH value is a characteristic number, ranging from pH 0 to pH 14, which indirectly shows the content of acidic or alkaline substances in a product.</p> <p>pH values less than 7 indicate sources of acidic substances, and values greater than 7 indicate sources of alkaline substances.</p> <p>To avoid irritation or chemical burns to the skin, the pH value of products must be in the range of human skin— approximately pH 5.5.</p> <p>G-Star recommends the limits cited to comply with global regulations and to minimize the chances of Chromium VI formation during tanning and processing of leather.</p> <p>For chrome-tanned leather, the final fixing bath of the re-tanning process should always have a pH below 4.0 to guard against the formation of Chromium VI.</p> <p>Important: Egypt, Morocco, and the Gulf Cooperation Council (GCC) require pH for leather not lower than 3.5.</p>

Restricted Substances List version 5.0				
CHEMICAL SUBSTANCE	CAS NUMBER	TEST METHOD	G-STAR RESTRICTED LIMIT	RELEVANCE OF RESTRICTION
ALKYLPHENOLS (APs) AND ALKYPHENOL ETHOXYLATES (APEOs)				
Nonylphenols (NP), mixed isomers	Various	Textiles and Leather: EN ISO 21084:2019 Polymers and all other materials: 1 g sample/20 mL THF, sonication for 60 minutes at 70 degrees C, analysis according to EN ISO 21084:2019	Total APs: 10 mg/kg Total APs + APEOs: 100 mg/kg	<p>APEOs can be used as or found in detergents, scouring agents, spinning oils, wetting agents, softeners, emulsifying/dispersing agents for dyes and prints, impregnating agents, de-gumming for silk production, dyes and pigment preparations, polyester padding and down/feather fillings.</p> <p>APs are used as intermediaries in the manufacture of APEOs and antioxidants used to protect or stabilize polymers. Biodegradation of APEOs into APs is the main source of APs in the environment.</p> <p>APEOs and formulations containing APEOs are prohibited from use throughout supply chain and manufacturing processes. We acknowledge that residual or trace concentrations of APEOs may still be found at levels exceeding 100 mg/kg and that more time is necessary for the supply chain to phase them out completely.</p> <p>Recycled products: Contact the G-Star Quality department for information about potential exemptions from the limit on NPEOs in recycled textile products.</p>
Octylphenols (OP), mixed isomers	Various	Down (China market only): GB/T 23322-2018 for compliance with GB/T 14272-2021		
Nonylphenol ethoxylates (NPEOs)	Various	All materials except Leather: EN ISO 18254-1:2016 with determination of APEO using LC/MS or LC/MS/MS Leather: Sample prep and analysis using EN ISO 18218-1:2023 with quantification according to EN ISO 18254-1:2016		
Octylphenol ethoxylates (OPEOs)	Various	Down (China market only): GB/T 23322-2018 for compliance with GB/T 14272-2021		

Restricted Substances List version 5.0				
CHEMICAL SUBSTANCE	CAS NUMBER	TEST METHOD	G-STAR RESTRICTED LIMIT	RELEVANCE OF RESTRICTION
AZO-AMINES AND ARYLAMINE SALTS				
4-Aminobiphenyl	92-67-1	<p>All materials except leather: EN ISO 14362-1:2017</p> <p>Leather: EN ISO 17234-1:2020</p> <p>4-Aminoazobenzene (4AAB):</p> <p>All materials except leather: EN ISO 14362-3:2017</p> <p>Leather: EN ISO 17234-2:2011</p>	< 20 mg/kg	<p>Azo dyes and pigments are colorants that incorporate one or several azo groups (-N=N-) bound with aromatic compounds.</p> <p>Thousands of azo dyes exist, but only those which degrade to form the listed cleaved amines are restricted.</p> <p>Azo dyes that release these amines are regulated and should no longer be used for dyeing textiles.</p>
Benzidine	92-87-5			
4-Chloro-o-toluidine	95-69-2			
2-Naphtylamine	91-59-8			
o-Aminoazotoluene	97-56-3			
2-Amino-4-nitrotoluene	99-55-8			
p-Chloraniline	106-47-8			
2,4-Diaminoanisol	615-05-4			
4,4'-Diaminodiphenylmethane (4,4'-MDA)	101-77-9			
3,3'-Dichlorobenzidine	91-94-1			
3,3'-Dimethoxybenzidine	119-90-4			
3,3'-Dimethylbenzidine	119-93-7			
3,3'-dimethyl-4,4'-diaminodiphenylmethane	838-88-0			
p-Cresidine	120-71-8			
4,4'-Methylen-bis(2-chloraniline)	101-14-4			
4,4'-Oxydianiline	101-80-4			
4,4'-Thiodianiline	139-65-1			
o-Toluidine	95-53-4			
2,4-Toluylendiamine (2,4-TDA)	95-80-7			
2,4,5-Trimethylaniline	137-17-7			
2-Methoxyaniline (= o-Anisidine)	90-04-0			
4-Aminoazobenzene (4-AAB)	60-09-3			
2,4-Xylidine	95-68-1			
2,6-Xylidine	87-62-7			
4-Chloro-o-toluidinium chloride	3165-93-3			
2-Naphthylammoniumacetate	553-00-4			
4-Methoxy-m-phenylene diammonium sulphate	39156-41-7			
2,4,5-Trimethylaniline hydrochloride	21436-97-5			

Restricted Substances List version 5.0				
CHEMICAL SUBSTANCE	CAS NUMBER	TEST METHOD	G-STAR RESTRICTED LIMIT	RELEVANCE OF RESTRICTION
BIOCIDES				
2-(Thiocyanomethylthio)- Benzothiazole (TCMTB)	21564-17-0	EN ISO 13365-1:2020	< 500 mg/kg	TCMTB is a preservative for leather and can be used as a pesticide
Triclosan	3380-34-5		< 50 mg/kg	Triclosan can be used as disinfectant and as antibacterial agent in textiles. Triclosan can damage the liver, kidneys, heart and lungs, suppresses the immune system.
2-Octylisothiazol-3(2H)- on (OIT)	26530-20-1		< 250 mg/kg	These chemicals have biocidal properties and can also be used as pesticides
4-Chlor-3-Methylphenol (CMK)	59-50-7		Leather: < 600 mg/kg	
Preservatives	Various	Chromatographic Methods and/or Methods US EPA 8081A, US EPA 8081B and US EPA 8151A	Forbidden	

Restricted Substances List version 5.0				
CHEMICAL SUBSTANCE	CAS NUMBER	TEST METHOD	G-STAR RESTRICTED LIMIT	RELEVANCE OF RESTRICTION
BISPHENOLS				
Bisphenol-A (BPA)	80-05-7	<div>Leather: EN ISO 11936:2023</div> <div>All other materials:</div> <div>Extraction: 1 g sample/20 ml THF, sonication for 60 minutes at 60 degrees C, then add methanol or acetonitrile for precipitation prior to analysis with LC/MS</div>	< 1 mg/kg	BPA may be used in the production of epoxy resins, polycarbonate plastics, flame retardants, and PVC. BPS may be used as a substitute for BPA and can be found along with BPF in polyamide dye-fixing agents and sulfone- and phenolbased leather tanning agents.
Bisphenol S (BPS)	80-09-1			BPA and BPS can be found in recycled polymeric and paper materials due to polycarbonate plastic and thermal receipt paper made with bisphenols entering waste streams.
Bisphenol B (BPB)	77-40-7			BPA, BPS, and BPB are included on the REACH SVHC list. Additional restrictions on the entire class of bisphenols are expected, with a revised restriction proposal forthcoming in the European Union.
Bisphenol F (BPF)	620-92-8			G-Star recommends testing relevant materials for bisphenols according to the Testing Matrix and to begin working with suppliers to minimize residual concentrations or replace them with better alternatives where possible.
CHLORINATED PARAFFINS				
Short-chain Chlorinated Paraffins (SCCPs) (C10-C13)	85535-84-8	<div>Leather:</div> <div>ISO 18219-1:2021 (SCCP)</div> <div>ISO 18219-2:2021 (MCCP)</div>	< 1000 mg/kg	May be used as softeners, flame retardants, or fat-liquoring agents in leather production; also as a plasticizer in polymer production.
Medium-chain Chlorinated Paraffins (MCCPs) (C14-C17)	85535-85-9	<div>Textiles and all other materials:</div> <div>ISO 22818:2021 (SCCP + MCCP)</div>	< 1000 mg/kg	

Restricted Substances List version 5.0				
CHEMICAL SUBSTANCE	CAS NUMBER	TEST METHOD	G-STAR RESTRICTED LIMIT	RELEVANCE OF RESTRICTION
CHLOROPHENOLS				
Pentachlorophenol (PCP)	87-86-5	All materials: EN 17134-2:2023	< 0.5 mg/kg each	<p>Chlorophenols are polychlorinated compounds used as preservatives or pesticides.</p> <p>Pentachlorophenol (PCP), Tetrachlorophenol (TeCP), and Trichlorophenols (TriCP) are sometimes used to prevent mold and kill insects when growing cotton and when storing/transporting fabrics.</p> <p>PCP, TeCP, and TriCP can also be used as in-can preservatives in print pastes and other chemical mixtures.</p>
2,3,5,6- Tetrachlorophenol (TeCP)	935-95-5			
2,3,4,6- Tetrachlorophenol (TeCP)	58-90-2			
2,3,4,5- Tetrachlorophenol (TeCP)	4901-51-3			
2,3,4-Trichlorophenol (TriCP)	15950-66-0			
2,3,5-Trichlorophenol (TriCP)	933-78-8			
2,3,6-Trichlorophenol (TriCP)	933-75-5			
2,4,5-Trichlorophenol (TriCP)	95-95-4			
2,4,6-Trichlorophenol (TriCP))	88-06-2			
3,4,5-Trichlorophenol (TriCP)	609-19-8			

Restricted Substances List version 5.0				
CHEMICAL SUBSTANCE	CAS NUMBER	TEST METHOD	G-STAR RESTRICTED LIMIT	RELEVANCE OF RESTRICTION
CHLORINATED BENZENES AND TOLUENES				
Hexachlorobenzene (HCB)	118-74-1	All materials: EN 17137:2018	< 1 mg / kg (total)	<p>Chlorobenzenes and Chlorotoluenes (Chlorinated Aromatic Hydrocarbons) can be used as carriers in the dyeing process of polyester or wool/ polyester fibers.</p> <p>They can also be used as solvents.</p> <p>Cross-contamination from anti-moth agents and poly shipping bags may cause failures.</p> <p>¹Important: The Gulf Cooperation Council (GCC) maintains a limit of 1 mg/kg for 1,2-Dichlorobenzene in textiles.</p>
Pentachlorobenzenes (PCB)	608-93-5			
$\alpha,\alpha,\alpha,4$ -tetrachlorotoluene; p-chlorobenzotrichloride	5216-25-1			
α,α,α -trichlorotoluene; benzotrichloride	98-07-7			
α -chlorotoluene; benzyl chloride	100-44-7			
1,2,3-Trichlorobenzene	87-61-6			
1,2,4-Trichlorobenzene	120-82-1			
1,3,5-Trichlorobenzene	108-70-3			
1,2,3,4-Tetrachlorobenzene	634-66-2			
1,2,3,5-Tetrachlorobenzene	634-90-2			
1,2,4,5-Tetrachlorobenzene	95-94-3			
1,3-Dichlorobenzene	541-73-1			
1-4-Dichlorobenzene	106-46-7			
2-Chlorotoluene	95-49-8			
3-Chlorotoluene	108-41-8			
4-Chlorotoluene	106-43-4			
2,3-Dichlorotoluene	32768-54-0			
2,4-Dichlorotoluene	95-73-8			
2,5-Dichlorotoluene	19398-61-9			
2,6-Dichlorotoluene	118-69-4			
3,4-Dichlorotoluene	95-75-0			
2,3,6-Trichlorotoluene	2077-46-5			
2,4,5-Trichlorotoluene	6639-30-1			
2,3,4,5-Tetrachlorotoluene	76057-12-0			
2,3,4,6-Tetrachlorotoluene	875-40-1			
2,3,5,6-Tetrachlorotoluene	1006-31-1			
Pentachlorotoluenes	877-11-2			
1,2-Dichlorobenzene	95-50-1		< 10 mg/kg ¹	

Restricted Substances List version 5.0				
CHEMICAL SUBSTANCE	CAS NUMBER	TEST METHOD	G-STAR RESTRICTED LIMIT	RELEVANCE OF RESTRICTION
DIMETHYLFUMARATE (DMFu)				
Dimethylfumarate (DMFu)	624-49-7	All materials: ISO 16186:2021	< 0.1 mg/kg	DMFu is an anti-mold agent that may be used in sachets in packaging to prevent the buildup of mold, especially during shipping.

Restricted Substances List version 5.0				
CHEMICAL SUBSTANCE	CAS NUMBER	TEST METHOD	G-STAR RESTRICTED LIMIT	RELEVANCE OF RESTRICTION
DISPERSE DYES WHICH ARE CLASSIFIED TO BE ALLERGENIC				
C.I. Disperse Blue 1	2475-45-8	All materials: DIN 54231:2022	< 30 mg/kg	<p>Disperse dyes are a class of water- insoluble dyes that penetrate the fiber system of synthetic or manufactured fibers and are held in place by physical forces without forming chemical bonds.</p> <p>Disperse dyes are used in synthetic fiber (e.g., polyester, acetate, polyamide).</p> <p>Restricted disperse dyes are suspected of causing allergic reactions and are prohibited from use for dyeing of textiles.</p>
C.I. Disperse Blue 3	2475-46-9			
C.I. Disperse Blue 7	3179-90-6			
C.I. Disperse Blue 26	3860-63-7			
C.I. Disperse Blue 35A	56524-77-7			
C.I. Disperse Blue 35B	56524-76-6			
C.I. Disperse Blue 102	12222-97-8			
C.I. Disperse Blue 106	12223-01-7			
C.I. Disperse Blue 124	61951-51-7			
C.I. Disperse Brown 1	23355-64-8			
C.I. Disperse Orange 1	2581-69-3			
C.I. Disperse Orange 3	730-40-5			
C.I. Disperse Orange 11	82-28-0			
C.I. Disperse Orange 149	85136-74-9			
C.I. Disperse Orange 37/59/76	12223-33-5 13301-61-6 51811-42-8			
C.I. Disperse Red 1	2872-52-8			
C.I. Disperse Red 11	2872-48-2			
C.I. Disperse Red 17	3179-89-3			
C.I. Disperse Red 151	61968-47-6			
C.I. Disperse Yellow 1	119-15-3			
C.I. Disperse Yellow 3	2832-40-8			
C.I. Disperse Yellow 7	6300-37-4			
C.I. Disperse Yellow 9	6373-73-5			
C.I. Disperse Yellow 23	6250-23-3			
C.I. Disperse Yellow 39	12236-29-2			
C.I. Disperse Yellow 49	54824-37-2 6858-49-7			
C.I. Disperse Yellow 56	54077-16-6			

Restricted Substances List version 5.0				
CHEMICAL SUBSTANCE	CAS NUMBER	TEST METHOD	G-STAR RESTRICTED LIMIT	RELEVANCE OF RESTRICTION
DYES WHICH ARE CLASSIFIED TO BE CARCINOGENIC				
C.I. Basic Red 9	569-61-9	All materials: DIN 54231:2022	< 30 mg/kg	Basic dyes are water- soluble cationic dyes mainly used on acrylic fibers.
C.I. Basic Violet 1	8004-87-3			
C.I. Basic Violet 3 (with ≥ 0.1 % Michler's ketone or base)	548-62-9			
C.I. Basic Violet 14	632-99-5			
C.I. Basic Blue 26 (with ≥ 0.1 % Michler's ketone or base)	2580-56-5			
C.I. Basic Green 4 (oxalate, chloride or free)	2437-29-8 569-64-2 10309-95-2			
C.I. Acid Red 26	3761-53-3			Acid dyes are water-soluble anionic dyes mainly used on fibers such as wool, silk, and nylon.
C.I. Acid Violet 49	1694-09-3			
C.I. Direct Black 38	1937-37-7			
C.I. Direct Blue 6	2602-46-2			
C.I. Direct Brown 95	16071-86-6			Direct dyes are used on natural fibers such as cotton, linen, cellulose and in special treatments such as dip dyes.
C.I. Direct Red 28	573-58-0			
4-Dimethylaminoazobenzene (Solvent Yellow 2)	60-11-7			Solvent dyes are dyes which are soluble in organic solvents, and can be used on natural and synthetic fibers.
C.I. Solvent Blue 4	6786-83-0			
Solvent Yellow 14	842-07-9			
4,4'-bis(dimethylamino)-4''-(methylamino)trityl alcohol (C.I. Violet 8)	561-41-1			
DYES NAVY BLUE				
Component 1: C39H23ClCrN7O12S.2Na Component 2: C46H30CrN10O20S2.3Na	118685-33-9 Not allocated	All materials: DIN 54231:2022	< 30 mg/kg	Navy blue colorants are regulated and prohibited from use for dyeing of textiles.

Restricted Substances List version 5.0				
CHEMICAL SUBSTANCE	CAS NUMBER	TEST METHOD	G-STAR RESTRICTED LIMIT	RELEVANCE OF RESTRICTION
FLAME RETARDANTS				
Tri(2,3-dibromopropyl)phosphate (TRIS)	126-72-7	EN ISO 17881-1 (2016) for brominated flame retardants EN ISO-17881-2 (2016) for phosphorus flame retardants	< 10 mg/kg each	<p>With very limited exceptions, flameretardant substances, including the entire class of organohalogen flame retardants, should no longer be applied to materials during production.</p> <p>Listed here are examples of lame-retardant substances used historically across the apparel and footwear industry. It is not intended to be a complete list. Other flame retardants not applicable to this industry are regulated worldwide by the Stockholm Convention and the Aarhus Protocol, which have been implemented in the European Union under the POPs Regulation.</p> <p>The 10 mg/kg limit is established to account for incidental impurities, byproducts, and contaminants. Flame retardants should not be used for any other purpose, e.g., as softeners or plasticizers.</p>
Tris(aziridinyl)phosphin oxide (TEPA)	545-55-1			
Polybromobiphenyls (PBBs)	59536-65-1			
Octabromodiphenylethers (OctaBDEs)	32536-52-0			
Polybrominated diphenyl ethers (PBDEs)	Various			
Decabromodiphenylether (DecaBDE)	1163-19-5			
Heptabromodiphenylethers (HeptaBDEs)	68928-80-3			
Tetrabromodiphenylethers (TetraBDEs)	40088-97-1			
Pentabromodiphenylethers (PentaBDEs)	32534-81-9			
Hexabromodiphenylethers (HexaBDEs)	36483-60-0			
Hexabromocyclododecane and all main diastereomers identified (alpha-, beta-, gamma-) (HBCDD)	3194-55-6 134237-50-6 134237-51-7 134237-52-8 25637-99-4			
Decabromodiphenyl ethane (DBDPE)	84852-53-9			
Tetrabromobisphenol A (TBBPA)	79-94-7			
Bis(2,3-dibromopropyl)phosphate (BIS)	5412-25-9			
2,2-Bis(bromomethyl)-1,3-propanediol (BBMP)	3296-90-0			
Trixylylphosphate (TXP)	25155-23-1			
Tris(1,3-dichloro-iso-propyl)phosphate (TDCPP)	13674-87-8			
Tris(2-chloroethyl)phosphate (TCEP)	115-96-8			
Tris (2-chloroisopropyl) phosphate	13674-84-5			

Restricted Substances List version 5.0				
CHEMICAL SUBSTANCE	CAS NUMBER	TEST METHOD	G-STAR RESTRICTED LIMIT	RELEVANCE OF RESTRICTION
FLUORINATED GREENHOUSE GASES				
Various	Various	<p>Sample preparation: Purge and trap — thermal desorption or SPME Measurement: GC/MS</p>	< 0.1 mg/kg	<p>Prohibited from use.</p> <p>May be used as foam blowing agents, solvents, fire retardants, and aerosol propellants.</p>
FORMALDEHYDE				
Formaldehyde	50-00-0	<p>All materials except Leather: JIS L 1041-2011 A (Japan Law 112) or EN ISO 14184-1:2011</p> <p>Leather: EN ISO 17226-2:2019 with EN ISO 17226- 1:2021 confirmation method in case of interferences.</p> <p>Alternatively, EN ISO 17226-1:2021 can be used on its own.</p>	< 75 mg/kg	Used in textiles as an anti-creasing and anti-shrinking agent. It is also often used in polymeric resins.

Restricted Substances List version 5.0				
CHEMICAL SUBSTANCE	CAS NUMBER	TEST METHOD	G-STAR RESTRICTED LIMIT	RELEVANCE OF RESTRICTION
HEAVY METALS EXTRACTABLE				
Chromium VI (Cr VI) and its compounds	18540-29-9	EN 16711-2:2016 EN ISO 17075-1:2017 if Cr is detected	< 1.0 mg/kg	Though typically associated with leather tanning, Chromium VI also may be used in the “after-chroming” process for wool dyeing (Chrome salts applied to acid-dyed wool to improve fastness).
Arsenic (As) and its compounds	7440-38-2	All materials except Leather: DIN EN16711-2:2016 Leather: DIN EN ISO 17072-1:2019 ² Crystal or “lead glass” is exempt from total Lead restrictions.	< 0.2 mg/kg	Arsenic and its compounds can be used in preservatives, pesticides, and defoliants for cotton, synthetic fibers, paints, inks, trims, and plastics.
Cadmium (Cd) and its compounds	7440-43-9		< 0.1 mg/kg	Cadmium compounds are used as pigments (especially in red, orange, yellow and green); as a stabilizer for PVC; and in fertilizers, biocides, and paints.
Lead (Pb) and its compounds	7439-92-1		< 1.0 mg/kg ²	Lead may be associated with plastics, paints, inks, pigments and surface coatings.
Antimony (Sb)	7440-36-0		< 30 mg/kg	Antimony can be found in or used as a catalyst in polymerization of polyester, flame retardants, fixing agents, pigments, and alloys.
Barium (Ba)	7440-39-3		< 1000 mg/kg	Barium and its compounds can be used in pigments for inks, plastics, and surface coatings, as well as in dyeing, mordants, filler in plastics, textile finishes, and leather tanning.
Cobalt (Co)	7440-48-4		< 4.0 mg/kg	Cobalt and its compounds can be used in alloys, pigments, dyestuff, and the production of plastic buttons.
Copper (Cu)	7440-50-8		< 50.0 mg/kg ³ ³ Copper is exempt from restriction limits in Metal parts	Copper and its compounds can be found in alloys and pigments, and in textiles as an antimicrobial agent.

Restricted Substances List version 5.0				
CHEMICAL SUBSTANCE	CAS NUMBER	TEST METHOD	G-STAR RESTRICTED LIMIT	RELEVANCE OF RESTRICTION
HEAVY METALS EXTRACTABLE CONTINUED				
Nickel (Ni)	7440-02-0	All materials except Leather: DIN EN 16711-2:2016 Leather: DIN EN ISO 17072-1:2019	< 1.0 mg/kg	Nickel and its compounds can be used for plating alloys and improving corrosion-resistance and hardness of alloys. They can also occur as impurities in pigments and alloys.
Chromium (Cr)	7440-47-3		< 2.0 mg/kg Leather: < 200 mg/kg	Chromium compounds can be used as dyeing additives; dye-fixing agents; colour-fastness after- treatments; dyes for wool, silk, and polyamide (especially dark shades); and leather tanning.
Mercury (Hg)	7439-97-6		< 0.02 mg/kg	Mercury compounds can be present in pesticides and as contaminants in caustic soda (NaOH). They may also be used in paints and as catalysts in the manufacture of PU and vinyl chloride for use in PVC.
Selenium (Se)	7782-49-2		< 500 mg/kg	Selenium may be found in synthetic fibres, paints, inks, plastics and metal trims.
APPLICABLE FOR LEATHER				
Chromium VI (Cr VI)	18540-29-9	EN ISO 17075-1:2017 and EN ISO 17075-2:2017 for confirmation in case the extract causes interference. Alternatively, EN ISO 17075-2:2017 may be used on its own. Aging of the sample is required according to ISO 10195 (2018) Method A2 (24h, 80°C, max. 10%rH, usage of a non- ventilated oven)	Not detected Detection Limit: 3 mg/kg	Many heavy metals are bio accumulative when absorbed by the human body through perspiration and give cause for concern in health terms such as chronic toxicity, allergenic reactions and cancer.
HEAVY METALS TOTAL CONTENT				
Cadmium (Cd)	7440-43-9	All materials except Leather: DIN EN 16711-1:2016 Leather: DIN EN ISO 17072-2:2019	< 40 mg/kg	Heavy metals, including arsenic, cadmium, lead, and mercury may be found in pigments and dyes, metal alloys and coating, and in the PVC stabilization process. Cadmium may be found in low quality dyes. Arsenic, cadmium, lead, and mercury may be found in pigments, but have largely been phased out. Metal alloys and coatings may contain arsenic, cadmium, and lead.
Mercury (Hg)	7439-97-6		< 0.5 mg/kg	
Arsenic (As)	7440-38-2		< 100 mg/kg	
Lead (Pb)	7439-92-1	Non-metal: CPSC-CH-E1002-08.3 Metal: CPSC-CH-E1001-08.3 Lead in paint and surface coatings: CPSC-CH-E1003-09.1	< 90 mg/kg	PVC stabilization may be accomplished with the use of cadmium or lead.

Restricted Substances List version 5.0				
CHEMICAL SUBSTANCE	CAS NUMBER	TEST METHOD	G-STAR RESTRICTED LIMIT	RELEVANCE OF RESTRICTION
HEAVY METALS RELEASABLE NICKEL				
Nickel	7440-02-0	Nickel release EN 1811: 2023 and Abrasion of coated items EN 12472: 2020	Release (metal parts): Prolonged skin contact: 0.5 µg/cm2/week Pierced part: 0.2 µg/cm2/week Eyewear frames: 0.5 µg/cm2/week	Nickel and its compounds can be used for plating alloys and improving corrosion-resistance and hardness of alloys. They can also occur as impurities in pigments and alloys.
		Release (eyewear frames): EN 16128:2015		
MONOMERS				
Styrene, Free	100-42-5	Extraction in Methanol GC/MS, sonication at 60 degrees C for 60 minutes	< 30 mg/kg	Styrene is a precursor for polymerization and may be present in various Styrene copolymers like plastic buttons. Free styrene is restricted, not total styrene.
Vinyl Chloride	75-01-4	EN ISO 6401:2008	< 1 mg/kg	Vinyl Chloride is a precursor for polymerization and may be present in various PVC materials like prints, coatings, flip flops, and synthetic leather.

Restricted Substances List version 5.0				
CHEMICAL SUBSTANCE	CAS NUMBER	TEST METHOD	G-STAR RESTRICTED LIMIT	RELEVANCE OF RESTRICTION
N-NITROSAMINES				
N-Nitrosodibutylamine (NDBA)	924-16-3	EN ISO 19577:2019 with LC/MS/MS verification if positive	< 0.5 mg/kg	Can be formed as by-product in the production of rubber.
N-Nitrosodiethylamine (NDEA)	55-18-5			
N-Nitrosodimethylamine (NDMA)	62-75-9			
N-Nitrosodipropylamine (NDPA)	621-64-7			
N-Nitrosomorpholine (NMOR)	59-89-2			
N-Nitroso-N-ethyl-N-phenylamine (NEPhA)	612-64-6			
N-Nitroso-N-methyl-N-phenylamine (NMPPhA)	614-00-6			
N-Nitroso-piperidine (NPIP)	100-75-4			
N-Nitroso-pyrrolidine (NPYR)	930-55-2			

Restricted Substances List version 5.0				
CHEMICAL SUBSTANCE	CAS NUMBER	TEST METHOD	G-STAR RESTRICTED LIMIT	RELEVANCE OF RESTRICTION
ORGANOTIN COMPOUNDS				
Tributyltin (TBT)	Various	All materials: CEN ISO/TS 16179:2012 or EN ISO 22744-1:2020	< 0.5 mg/kg	Class of chemicals combining tin and organics such as butyl and phenyl groups that should no longer be used in the production of apparel, footwear, and related products. Organotins are predominantly found in the environment as antifoulants in marine paints, but they can also be used as biocides (e.g., antibacterials), catalysts in plastic and glue production, and heat stabilizers in plastics/rubber. In textiles and apparel, organotins are associated with plastics/rubber, inks, paints, metallic glitter, polyurethane products and heat transfer material. G-star recommends restricting “Other Organotins” as a matter of best practice consistent with other industry restricted substances lists.
Triphenyltin (TPhT)	Various		< 1 mg/kg each	
Dibutyltin (DBT)	Various			
Diocetyltn (DOT)	Various			
Monobutyltin (MBT)	Various			
Tricyclohexyltin (TCyHT)	Various			
Triocetyltn (TOT)	Various			
Tripropyltin (TPT)	Various			
Trimethyltin (TMT)	Various		Other organotins: < 1 mg/kg each	
Monoocetyltn (MOT)	Various			
Dimethyltin (DMT)	Various			
Diphenyltin (DPhT)	Various			
Dipropyltin (DPT)	Various			
Monomethyltin (MMT)	Various			
Monophenyltin (MPhT)	Various			
Tetrabutyltin (TeBT)	1461-25-2			
Tetraethyltin (TeET)	597-64-8			
Tetraocetyltn (TeOT)	3590-84-9			
ORTHO-PHENYLPNENOL (OPP)				
o-Phenylphenol (OPP)	90-43-7	All materials: EN 17134-2:2023	< 100 mg/kg Leather < 1000 mg/kg	OPP is used for its preservative properties in leather or as a carrier in polyester dyeing processes.
OZONE DEPLETING SUBSTANCES				
Various	Various	GC-MS headspace 120° C for 45 minutes	< 5 mg/kg	Prohibited from use. Ozone-depleting substances have been used as a foaming agent in PU foams as well as a dry-cleaning agent.

Restricted Substances List version 5.0				
CHEMICAL SUBSTANCE	CAS NUMBER	TEST METHOD	G-STAR RESTRICTED LIMIT	RELEVANCE OF RESTRICTION
PER-AND POLYFLUOROALKYL SUBSTANCES (PFAS)⁵ (SEE APPENDIX A FOR INDIVIDUAL SUBSTANCES)				
All PFAS as measured by total organic fluorine	Various	EN 14582:2016 or ASTM D7359:2023	100 mg/kg by 2023 50 mg/kg by 2027	<p>PFAS may be used in commercial water-, oil-, and stain-repellent agents as well as in breathable membranes that remove moisture, e.g., PTFE.</p> <p>Regulations around the world ban the use of PFAS in apparel and footwear, with partial or full exemptions for personal protective equipment and outdoor apparel for severe wet conditions.</p> <p>Refer to Appendix A for a list of PFAS substances and CAS Numbers for which testing can be conducted to indicate whether PFAS chemistry is present above restricted levels due to intended use or unintended contamination.</p>
Perfluorooctane Sulfonate (PFOS) and related substances ⁶	Various	All materials: EN ISO 23702-1:2023 or EN 17681-1:2022 & 17681-2:2022	< 1 µg/m2 total	
Perfluorooctanoic Acid (PFOA) and its salts	Various		< 0.025 mg/kg total	
PFOA-related substances	Various		< 1 mg/kg total	
Perfluorohexane-1-sulphonic acid (PFHxS) and its salts	Various		< 0.025 mg/kg total	
PFHxS-related substances	Various		< 1 mg/kg total	
C9-C14 Perfluorocarboxylic acids (PFCAs) and their salts	Various		< 0.025 mg/kg total	
C9-C14 PFCA-related substances	Various		< 0.26 mg/kg total	
PFHxA, its salts, and related substances	Various		Anticipated regulated limits in the EU: PFHxA and its salts: < 0.025 mg/kg PFHxA-related substances: < 1 mg/kg	
<p>⁶The 1 µg/m2 total area-based limit for PFOS and related substances is in the process of revision under the EU POPs Regulation and will transition to a 25 ppb total sum limit on PFOS and its salts and a 1000 ppb total sum limit on PFOS-related substances. This will bring EU PFOS restrictions into alignment with other existing PFAS restrictions included here.</p> <p>Important note: New draft updated method prEN 17681-1:2023 for targeted PFAS analysis is likely to be finalized and adopted in a future version of the G-Star RSL. G-Star anticipates higher findings of various PFAS analytes, especially FTOHs, with this new method, and industry should prepare accordingly</p>				

Restricted Substances List version 5.0				
CHEMICAL SUBSTANCE	CAS NUMBER	TEST METHOD	G-STAR RESTRICTED LIMIT	RELEVANCE OF RESTRICTION
PESTICIDES AGRICULTURAL (SEE APPENDIX B FOR INDIVIDUAL SUBSTANCES)				
See Appendix B for the complete list	Various	All materials: EN ISO 15913:2003 or EPA 8081/EPA 8151A or BVL L 00.00-34:2010-09	< 0.5 mg/kg	May be found in natural fibers, primarily cotton.
PHthalATES				
Bis(2-ethylhexyl) phthalate (DEHP)	117-81-7	<p>Sample preparation for all materials: CPSC-CH-C1001-09.4</p> <p>Measurement:</p> <p>Textiles: GC/MS, EN ISO 14389:2022 (8.1 Calculation based on weight of print only; 8.2 Calculation based on weight of print and textile if print cannot be removed).</p> <p>All materials except textiles: GC/MS</p>	<p>< 500 mg/kg each</p> <p>The sum of all Phthalates < 1000 mg/kg</p>	<p>Esters of ortho-phthalic acid (Phthalates) are a class of organic compound commonly added to plastics to increase flexibility.</p> <p>They are sometimes used to facilitate the molding of plastic by decreasing its melting temperature.</p> <p>Phthalates can be found in:</p> <ul style="list-style-type: none"> • Flexible plastic components (e.g., PVC) <ul style="list-style-type: none"> • Print pastes • Adhesives • Plastic buttons • Plastic sleeveings • Polymeric coatings <p>Listed here are all legally restricted phthalates as well as those included on the REACH substances of very high concern (SVHC) candidate list at the time of publication. Suppliers should assume that the RSL includes all phthalates on the SVHC list—whether itemized here or not— since the list is updated frequently.</p>
Dibutyl phthalate (DBP)	84-74-2			
Butylbenzyl phthalate (BBP)	85-68-7			
Di-isobutyl phthalate (DIBP)	84-69-5			
Di-“isononyl” phthalate (DINP)	28553-12-0 68515-48-0			
Di-“isodecyl” phthalate (DIDP)	26761-40-0 68515-49-1			
Di-n-octyl phthalate (DNOP)	117-84-0			
1,2-Benzenedicarboxylic acid, di-C6-8-branched alkyl esters, C7-rich (DIHP)	71888-89-6			
Di-isopentylphthalate (DIPP)	605-50-5			
Di-n-pentyl phthalate (DPP)	131-18-0			
Bis(2-methoxyethyl) phthalate (DMEP)	117-82-8			
Di-n-hexyl phthalate (DnHP)	84-75-3			

Restricted Substances List version 5.0				
CHEMICAL SUBSTANCE	CAS NUMBER	TEST METHOD	G-STAR RESTRICTED LIMIT	RELEVANCE OF RESTRICTION
PHthalates CONTINUED				
1,2-Benzenedicarboxylic acid Dipentyl ester, branched and linear	84777-06-0	<p>Sample preparation for all materials: CPSC-CH-C1001-09.4</p> <p>Measurement:</p> <p>Textiles: GC/MS, EN ISO 14389:2022</p> <p>(8.1 Calculation based on weight of print only; 8.2 Calculation based on weight of print and textile if print cannot be removed).</p> <p>All materials except textiles: GC/MS</p>	<p>< 500 mg/kg each</p> <p>The sum of all Phthalates < 1000 mg/kg</p>	<p>Esters of ortho-phthalic acid (Phthalates) are a class of organic compound commonly added to plastics to increase flexibility.</p> <p>They are sometimes used to facilitate the molding of plastic by decreasing its melting temperature.</p> <p>Phthalates can be found in:</p> <ul style="list-style-type: none"> • Flexible plastic components (e.g., PVC) <ul style="list-style-type: none"> • Print pastes • Adhesives • Plastic buttons • Plastic sleeveings • Polymeric coatings <p>Listed here are all legally restricted phthalates as well as those included on the REACH substances of very high concern (SVHC) candidate list at the time of publication. Suppliers should assume that the RSL includes all phthalates on the SVHC list—whether itemized here or not— since the list is updated frequently.</p>
1,2-Benzenedicarboxylic acid, di-C7-11-branched and linear alkyl esters (DHNUP)	68515-42-4			
N-pentyl-isopentyl phthalate (NPIPP)	776297- 69-9			
Di-cyclohexylphthalate (DCHP)	84-61-7			
Di-hexylphthalate, branched and linear (DHxP)	68515-50-4			
1,2-benzenedicarboxylic acid, di-C6-10-alkyl esters; 1,2-benzenedicarboxylic acid, mixed decyl and hexyl and octyl diesters with ≥ 0.3% of dihexyl phthalate (EC No. 201-559-5)	68515-51-5 68648-93-1			
Di-iso-hexylphthalate (DIHxP)	71850-09-4			
Di-n-propylphthalate (DPrP)	131-16-8			
Diethyl phthalate (DEP)	84-66-2			
Dimethyl phthalate (DMP)	131-11-3			
Di-iso-octyl phthalate (DIOP)	27554-26-3			
Bis(2-ethylhexyl) tetrabromophthalate	26040-51-7			

Restricted Substances List version 5.0				
CHEMICAL SUBSTANCE	CAS NUMBER	TEST METHOD	G-STAR RESTRICTED LIMIT	RELEVANCE OF RESTRICTION
POLYCYCLIC AROMATIC HYDROCARBONS (PAHs)				
Benzo(a)pyrene [BaP]	50-32-8	AfPS GS 2019 or EN 17132: 2019 or ISO 16190: 2021	1 mg/kg each	PAHs are natural components of crude oil and are common residues from oil refining. PAHs have a characteristic smell similar to that of car tires or asphalt. Oil residues containing PAHs are added to rubber and plastics as a softener or extender and may be found in rubber, plastics, lacquers and coatings.
Benzo(a)anthracene	56-55-3			
Chrysene	218-01-9			
Benzo(b)fluoranthene	205-99-2			
Benzo(k)fluoranthene	207-08-9			
Dibenzo(a,h)anthracene	53-70-3			
Benzo(e)pyrene	192-97-2			
Benzo(j)fluoranthene	205-82-3			
Acenaphthene	83-32-9		No individual restriction Total: < 10 mg/kg	PAHs are often found in the outsoles of footwear and in printing pastes for screen prints. PAHs can be present as impurities in Carbon Black. They also may be formed from thermal decomposition of recycled materials during reprocessing. ⁴ Naphthalene: Dispersing agents for textile dyes may contain high residual naphthalene concentrations due to the use of low-quality Naphthalene derivatives (e.g., poor- quality Naphthalene Sulphonate Formaldehyde condensation products).
Acenaphthylene	208-96-8			
Antracene	120-12-7			
Benzo(g,h,i)perylene	191-24-2			
Fluoranthene	206-44-0			
Fluorene	86-73-7			
Indeno(1,2,3-cd)pyrene	193-39-5			
Naphthalene ⁴	91-20-3			
Phenanthrene	85-01-8			
Pyrene	129-00-0			
QUINOLINE				
Quinoline	91-22-5	All materials: DIN 54231:2022 with methanol extraction at 70 degrees C	< 50 mg/kg	Found as an impurity in polyester and some dyestuffs. Quinoline can be included with disperse dye testing, as the same method is used for both. It is not expected in non-dyed materials.

Restricted Substances List version 5.0				
CHEMICAL SUBSTANCE	CAS NUMBER	TEST METHOD	G-STAR RESTRICTED LIMIT	RELEVANCE OF RESTRICTION
RESTRICTION ON PACKAGING				
Cadmium (Cd)	Various	CEN/TR 13695-1 Acid digestion with ICP analysis	The sum of concentration levels of lead, cadmium, mercury and hexavalent chromium present in packaging or packaging components shall not exceed 100 mg/kg	Packaging means transportation packaging as well as product packaging, i.e., any material used for the containment, protection, handling, delivery, and presentation of finished goods (article).
Lead (Pb)				
Chromium (Cr6+) - hexavalent				
Mercury (Hg)				
⁷ MOAH consisting of 1 to 7 aromatic rings		GC-FID/MS	< 1.0% 1 January 2025 onwards < 0.1% and <1 mg/kg MOAH compounds containing 3 to 7 aromatic rings)	These mineral oils can be used in printing inks of packaging materials and recycled paper. The implementation applies to mineral oils containing substances that disrupt the recycling of packaging waste paper or restrict the use of recycled materials because of the risk of these substances to human health.
⁷ MOSH consisting of 16 to 35 carbon atoms			< 0.1% (< 1000 mg/kg)	
Butylated Hydroxytoluene (BHT)	128-37-0	All materials: ASTM D4275	< 25 mg/kg	Used as an additive in plastics as an antioxidant to prevent aging. Can cause phenolic yellowing of textiles.
⁷ Suppliers should inform their contracted packaging and/or printing companies about the MOSH/MOAH restrictions in order that they determine, in consultation with printing ink manufacturers, the permissible printing inks (free of MOSH/MOAH) within the meaning of the Arrêté du 13 Avril 2022. A declaration of conformity, whilst not yet required, will be required in the future as part of the planned EU Packaging Regulation. As part of the duty of care as a manufacturer, random checks should be carried out on the printing inks used or the printed materials.				
SOLVENTS AND RESIDUALS				
DMFa (N,N Dimethylformamide)	68-12-2	Textiles: EN 17131:2019 All other materials: ISO 16189:2021	< 500 mg/kg	DMFa is a solvent used in plastics, rubber, and polyurethane (PU) coating. Water-based PU does not contain DMFa and is therefore preferable.
N-Methyl-2-pyrrolidone (NMP)	872-50-4		< 1000 mg/kg	Industrial solvent used in production of water-based Polyurethanes and other polymeric materials. May also be used as a surface treatment for textiles, resins, and metal-coated plastics, or as a paint stripper.
DMAC (N,N-dimethylacetamide)	127-19-5			Solvent used in the production of elastane fibers and sometimes as substitute for DMFa.
Formamide	75-12-7		< 200 mg/kg	Byproduct in the production of EVA foams.

Restricted Substances List version 5.0				
Chemical Substance	CAS Number	Test Method	G-Star Restricted Limit	Relevance of Restriction
UV Absorbers / Stabilisers				
2-benzotriazol-2-yl-4,6-di-tert- butylphenol (UV-320)	3846-71-7	ISO 24040: 2022 with extraction in THF, analysis by GC/MS	< 1000 mg/kg each	PU foam materials such as open cell foams for padding. Used as UV-absorbers for plastics (PVC, PET, PC, PA, ABS, and other polymers), rubber, polyurethane.
2,4-di-tert-butyl-6-(5- chlorobenzotriazol-2-yl)phenol (UV-327)	3864-99-1			
2-(2H-benzotriazol-2-yl)-4,6- ditertpentylphenol (UV-328)	25973-55-1			
2-(2H-benzotriazol-2-yl)-4-(tert-butyl)-6-(sec-butyl)phenol (UV-350)	36437-37-3			
Volatile Organic Compounds (VOCs)				
Benzene	71-43-2	For general VOC screening: GC/MS headspace 45 minutes at 120 degrees C	< 1 mg/kg	These VOCs should not be used in textile auxiliary chemical preparations. They are associated with solvent- based processes such as solvent-based polyurethane coatings and glues/adhesives. They should not be used for any kind of facility cleaning or spot cleaning.
Pentachloroethane	76-01-7		< 1000 mg/kg	
1,1,1,2- Tetrachloroethane	630-20-6		< 1000 mg/kg	
1,1,2,2- Tetrachloroethane	79-34-5		< 1000 mg/kg	
1,1,1- Trichloroethane	71-55-6		< 1000 mg/kg	
1,1,2- Trichloroethane	79-00-5		< 1000 mg/kg	
Toluene	108-88-3		< 10 mg/kg	
Carbon Disulfide	75-15-0		< 1000 mg/kg	
1,2-Dichloroethane	107-06-2		< 10 mg/kg	
1,1-Dichloroethylene	75-35-4		< 1000 mg/kg	
Ethylbenzene	100-41-4		< 50 mg/kg	
Xylene	1330-20-7		< 30 mg/kg	
Orthoxylene	95-47-6		< 1000 mg/kg	
Metaxylene	108-38-3		< 1000 mg/kg	
Paraxylene	106-42-3		< 1000 mg/kg	
Cyclohexanone	108-94-1		< 50 mg/kg	
2-Butanone (MEK)	78-93-3		< 50 mg/kg	
Tetrachloroethylene (PERC)	127-18-4		< 50 mg/kg	
Trichloroethylene	79-01-6		< 50 mg/kg	
Phenol	108-95-2		< 100 mg/kg	
Carbon Tetrachloride	56-23-5		< 1000 mg/kg	
Trichloromethane (Chloroform)	67-66-3		< 1000 mg/kg	

Appendix version 5.0					
SUBSTANCE	CAS NUMBER	SUBSTANCE	CAS NUMBER	SUBSTANCE	CAS NUMBER
APPENDIX A. PER-AND POLYFLUOROALKYL SUBSTANCES (PFAS)*					
PFOS and Related Substances		PFOA and Its Salts		PFHxS and its Salts	
Perfluorooctanesulfonic acid (PFOS)	1763-23-1	Perfluorooctanoic acid (PFOA)	335-67-1	Perfluorohexane Sulfonic acid (PFHxS)	355-46-4
Perfluorooctanesulfonic acid, potassium salt (PFOS-K)	2795-39-3	Sodium perfluorooctanoate (PFOA-Na)	335-95-5	Perfluorohexane Sulfonic acid, potassium salt (PFHxS-K)	3871-99-6
Perfluorooctanesulfonic acid, lithium salt (PFOS-Li)	29457-72-5	Potassium perfluorooctanoate (PFOA-K)	2395-00-8	Perfluorohexane Sulfonic acid, lithium salt (PFHxS-Li)	55120-77-9
Perfluorooctanesulfonic acid, ammonium salt (PFOS-NH ₄)	29081-56-9	Silver perfluorooctanoate (PFOA-Ag)	335-93-3	Perfluorohexane Sulfonic acid, ammonium salt (PFHxS-NH ₄)	68259-08-5
Perfluorooctane sulfonate diethanolamine salt (PFOS-NH(OH) ₂)	70225-14-8	Perfluorooctanoyl fluoride (PFOA-F)	335-66-0	Perfluorohexane Sulfonic acid, sodium salt (PFHxS-Na)	82382-12-5
Perfluorooctanesulfonic acid, tetraethylammonium salt (PFOS-N(C ₂ H ₅) ₄)	56773-42-3	Ammonium pentadecafluorooctanoate (APFO)	3825-26-1	PFHxS-related Substances	
Didecyldimethyl ammonium perfluorooctane sulfonate (PFOS-N(C ₁₀ H ₂₁) ₂ (CH ₃) ₂)	251099-16-8	PFOA-related Substances		N-Methylperfluoro-1-hexanesulfonamide (N-Me-FHxSA)	68259-15-4
N-Ethylperfluoro-1-octanesulfonamide (N-Et-FOSA)	4151-50-2	1H,1H,2H,2H-Perfluorodecanesulfonic acid (8:2 FTS)	39108-34-4	Perfluorohexane sulfonamide (PFHxSA)	41997-13-1
N-Methylperfluoro-1-octanesulfonamide (N-Me-FOSA)	31506-32-8	Methyl perfluorooctanoate (Me-PFOA)	376-27-2	*NOTE: This list is a subset of PFAS and is not exhaustive.	
2-(N-Ethylperfluoro-1-octanesulfonamido)-ethanol (N-Et-FOSE)	1691-99-2	Ethyl perfluorooctanoate (Et-PFOA)	3108-24-5		
2-(N-Methylperfluoro-1-octanesulfonamido)-ethanol (N-Me-FOSE)	24448-09-7	2-Perfluorooctylethanol (8:2 FTOH)	678-39-7		
Perfluoro-1-octanesulfonyl fluoride (POSF)	307-35-7	1H,1H,2H,2H-Perfluorodecyl acrylate (8:2 FTA)	27905-45-9		
Perfluorooctane sulfonamide (PFOSA)	754-91-6	1H,1H,2H,2H-Perfluorodecyl methacrylate (8:2 FTMA)	1996-88-9		
		2H,2H-Perfluorodecanoic acid (H ₂ PFDA)	27854-31-5		

Appendix version 5.0					
SUBSTANCE	CAS NUMBER	SUBSTANCE	CAS NUMBER	SUBSTANCE	CAS NUMBER
APPENDIX A. PER-AND POLYFLUOROALKYL SUBSTANCES (PFAS)* CONTINUED					
C9 – C14 PFCAs and Their Salts		C9 – C14 PFCA-related Substances		PFHxA, Its Salts, and Related Substances	
Perfluorotetradecanoic Acid (PFTeDA, C14-PFCA)	376-06-7	1H,1H,2H,2H-Perfluorododecyl acrylate (10:2 FTA)	17741-60-5	Perfluorohexanoic Acid (PFHxA, C6-PFCA)	307-24-4
Perfluoro-3-7-dimethyloctanecarboxylate (PF-3,7-DMOA)	172155-07-6	1H,1H,2H,2H-Perfluorododecyl methacrylate (10:2 FTMA)	2144-54-9	1H,1H,2H,2H-Perfluorooctanesulfonic acid (6:2 FTS)	27619-97-2
Perfluorononanoic Acid (PFNA, C9-PFCA)	375-95-1	1H,1H,2H,2H-Perfluorododecanol (10:2 FTOH)	865-86-1	1H,1H,2H,2H-Perfluorooctanol (6:2 FTOH)	647-42-7
Perfluorodecanoic Acid (PFDA, C10-PFCA)	335-76-2	2H,2H,3H,3H-Perufloroundecanoic acid (H4PFUnA)	34598-33-9	*NOTE: This list is a subset of PFAS and is not exhaustive.	
Perfluoroundecanoic Acid (PFUnA, C11-PFCA)	2058-94-8	Perfluorocylethanol 8:2 (8:2 FTOH)	678-39-7		
Perfluorododecanoic Acid (PFDoA, C12-PFCA)	307-55-1	1H,1H,2H,2H-perfluorotetradecan-1-ol (12:2 FTOH)	39239-77-5		
Perfluorotridecanoic Acid (PFTrDA, C13-PFCA)	72629-94-8	1H,1H,2H,2H-Perfluorododecanesulphonic acid (10:2 FTS)	120226-60-0		
		1H,1H,2H,2H-Perfluorododecyl iodide (10:2 FTI)	2043-54-1		
		1H,1H,2H,2H-Perfluorotetradecyl iodide (12:2 FTI)	30046-31-2		

Appendix version 5.0					
SUBSTANCE	CAS NUMBER	SUBSTANCE	CAS NUMBER	SUBSTANCE	CAS NUMBER
APPENDIX B. PESTICIDES AND HERBICIDES, AGRICULTURAL					
2-(2,4,5-trichlorophenoxy) propionic acid, its salts and compounds; 2,4,5-TP	93-72-1	Dichlofluanide	1085-98-9	Kelevane	4234-79-1
2,4,5-T	93-76-5	Dichlorprop	120-36-5	Kepone	143-50-0
2,4-D	94-75-7	Dicofol	115-32-2	Lindane	58-89-9
Aldrine	309-00-2	Dicrotophos	141-66-2	Malathione	121-75-5
Azinophosmethyl	86-50-0	Dieldrine	60-57-1	MCPA	94-74-6
Azinophosethyl	2642-71-9	Dimethoate	60-51-5	MCPB	94-81-5
Bromophos-ethyl	4824-78-6	Dinoseb, Salts and Acetate	88-85-7	Mecoprop	93-65-2
Captafol	2425-06-1	DTTB (4, 6-Dichloro-7 (2,4,5-trichloro- phenoxy) -2-Trifluoro methyl benz imidazole)	63405-99-2	Metamidophos	10265-92-6
Carbaryl	63-25-2	Endosulfan	115-29-7	Methoxychlor	72-43-5
Chlorbenzilat	510-15-6	Endosulfan, α-	959-98-8	Mirex	2385-85-5
Chlordane	57-74-9	Endosulfan, β-	33213-65-9	Monocrotophos	6923-22-4
Chlordimeform	6164-98-3	Endrine	72-20-8	Parathion-methyl	298-00-0
Chlorfenvinphos	470-90-6	Esfenvalerate	66230-04-4	Pentachloroanisole	1825-21-4
Chlorthalonil	1897-45-6	Ethylendibromid	106-93-4	Phosdrin/Mevinphos	7786-34-7
Coumaphos	56-72-4	Ethylparathione; Parathion	56-38-2	Perthane	72-56-0
Cyfluthrin	68359-37-5	Fenvalerate	51630-58-1	Propethamphos	31218-83-4
Cyhalothrin	91465-08-6	Halogenated naphthalenes, including polychlorinated naphthalenes (PCNs)	Various	Profenophos	41198-08-7
Cypermethrin	52315-07-8	Heptachlor	76-44-8	Quinalphos	13593-03-8
S,S,S-Tributyl phosphotriithioate (Tribufos)	78-48-8	Heptachlorepoxyde	1024-57-3	Quintozene	82-68-8
Deltamethrin	52918-63-5	Hexabromobiphenyl	36355-01-8	Strobane	8001-50-1
DDD	53-19-0 72-54-8	a-Hexachlorcyclohexane with & without Lindane	319-84-6	TelodrinE	297-78-9
DDE	3424-82-6 72-55-9	b-Hexachlorcyclohexane with & without Lindane	319-85-7	Toxaphene	8001-35-2
DDT	50-29-3 789-02-6	g-Hexachlorcyclohexane with & without Lindane	319-86-8	Tolyfluanide	731-27-1
Diazinon	333-41-5	Hexachlorobenzene	118-74-1	Trifluralin	1582-09-8
Polychlorinated naphthalenes	70776-03-3	Isodrine	465-73-6		

REACH Candidate List version 5.0
REACH CANDIDATE LIST
For suppliers that are doing wet processing or tanning in the EU the requirements of the Authorisation list must be met.
The full list of Substances Subject to Authorization can be found here-
https://echa.europa.eu/candidate-list-table
WHAT ALL SUPPLIERS AND SOURCES SHOULD DO
Every G-Star Supplier and Source agree to inform G-Star of any substances listed in the candidate present in any G-Star product with over 0.1% w/w (>1000 mg/kg). The European Court of Justice judgement of 10-09-2015 case C-106/14 is referring to every constituent part of the article. In supplying this information G-Star does not intend to assume all or any part of our Suppliers' and/or Sources' duty to comply with the regulation. Chemicals, substances and articles will be assessed on their risks for health and environmental aspects.
All G-Star Suppliers and Sources shall visit the European Chemicals Agency (ECHA) website (www.echa.europa.eu) regularly and comply with the published obligations and guidance regarding chemicals and consumer articles.
To help ensure that all products supplied to G-Star comply with REACH, each Supplier and Source is obligated to track not only the current SVHCs, as listed on the ECHA website, but also the entire list of potential SVHCs. Suppliers and Sources shall map each step in their supply chains, including the sourcing and processing of Materials, Chemicals and Other Goods ingredients, and immediately inform G-Star. according to the Information Duty (Article 33) of all cases where a substance listed in the Candidate List of Substances of Very High Concerns for Authorization is present in the product or other Materials, Chemicals and Other Goods provided for use in any G-Star labeled or distributed product. Additionally, authorization requirements (as per Annexure XIV) and restriction requirements (as per Annexure XVII) in REACH regulation shall be considered by any Suppliers or Sources situated in Europe.



Declaration of Conformity Form to G-STAR RSL (version 5.0)	
This Declaration of Conformity is issued under the sole responsibility of:	
Name of Supplier-	Address of Supplier -
Date of Declaration(validity 1 year)-	Product Group-
Name and Title of Contact-	SIGNATURE
<p>The above named Supplier declare that all products sold to G-Star comply with G-Star RSL requirements. G-Star reserve the right to audit products at random to ensure that Declarations of Conformity are valid.</p> <p>In case of failure, which means not complying with G-Star's RSL, the merchandise will not be accepted and the supplier will receive respective written information. There will be a fine to be paid by the supplier based on the damage G-Star suffered.</p>	

Change log version 5.0	
CHEMICAL GROUP (RSL)	CHANGE LOG MAJOR CHANGES FROM RSL 4.0 TO RSL 5.0
ACETEPHENONE AND 2-PHENYL-2-PROPANOL	No major changes
ACIDIC AND ALKALINE SUBSTANCES (pH)	Updated test method and relevance of restriction
ALKYLPHENOLS (AP) AND ALKYLPHENOL ETHOXYLATES (APEO)	Updated test method
ASBESTOS	Removed category
AZO AMINES AND ARYLAMINE SALTS	No major changes
BIOCIDES	Moved DMFu and OPP to their own categories
BISPHENOLS	Removed Bisphenol AF Updated test method Updated limits
CHLORINATED PARAFFINS	No major changes
CHLOROPHENOLS	Updated test method
CHLORINATED BENZENES AND TOLUENES	No major changes
DIMETHYLFUMARATE (DMFu)	Added new category
DISPERSE DYES WHICH ARE CLASSIFIED TO BE ALLERGENIC	Added CAS number for Disperse Yellow 49
DYES WHICH ARE CLASSIFIED TO BE CARCINOGENIC	No major changes
DYESTUFFS CARCINOGENIC AND WITH ENVIRONMENTAL PROBLEMS	Changed category name to DYES NAVY BLUE Updated relevance of restriction
FLAME RETARDANTS	Added 1 substance Updated relevance of restriction Updated limit for TCEP and TDCPP
FLUORINATED GREENHOUSE GASES	No major changes
FORMALDEHYDE	Updated test method
HEAVY METALS EXTRACTABLE	Updated relevance of restriction for Mercury
HEAVY METALS TOTAL CONTENT	No major changes
HEAVY METALS RELEASABLE NICKEL	Updated test method
MONOMERS	No major changes
N-NITROSAMINES	No major changes

Change log version 5.0	
CHEMICAL GROUP (RSL)	CHANGE LOG MAJOR CHANGES FROM RSL 4.0 TO RSL 5.0
ORGANOTIN COMPOUNDS	Added 9 substances Updated relevance of restriction
ORTHOPHEYLPHENOL (OPP)	Added new category Updated test method
OZONE DEPLETING SUBSTANCES	Updated test method
PER-AND POLYFLUOROALKYL SUBSTANCES (PFAS)	Updated overview based on latest information
PESTICIDES	Updated test method Updated limit
PHTHALATES	Added 1 substance Updated test method
POLYCYCLIC AROMATIC HYDROCARBONS (PAHs)	Updated test method
QUINOLINE	Updated relevance of restriction
RESTRICTION ON PACKAGING	No major changes
SOLVENTS AND RESIDUALS	No major changes
UV ABSORBERS / STABILISERS	Updated test method
VOLATILE ORGANIC COMPOUNDS (VOCs)	Updated limit for 13 substances
INTRODUCTION	No major changes
SUPPLIER RESPONSIBILITY	No major changes
DEFINITION OF MATERIAL TYPE	Updated based on latest information
RISK MATRIX APPAREL & FOOTWEAR	Updated based on latest information
RISK MATRIX PACKAGING	Updated based on latest information
APPENDICES	Updated based on latest information
REACH CANDIDATE LIST	No major changes
DECLARATION OF CONFORMITY	No major changes

DISCLAIMER
© G-Star Raw C.V. 2024
Information provided in this document is valid as of March 2024. Changes, modifications and/or actualizations will be notified from time to time, and will make part of this list as of such date.
For any questions or further information please contact RSL@g-star.com